

ACOUSTIC AND NON-ACOUSTIC PERFORMANCE OF COAL BOTTOM ASH  
AS SOUND ABSORPTIVE MATERIAL FOR REDUCING RAILWAY NOISE  
LEVEL

NURUL IZZATI RAIHAN BINTI RAMZI HANNAN

A thesis submitted in  
Fulfilment of the requirement for the award of the  
Doctor of Philosophy in Civil Engineering

Faculty of Civil and Environmental Engineering  
Universiti Tun Hussein Onn Malaysia

SEPTEMBER 2019

## DEDICATION

I dedicate this dissertation to my loving parent

Abah and Mama

My sweet husband Ahmad Fattah Al Islam

My sons

My supportive supervisor Ts. Dr. Shahiron Shahidan

Who has offered unwavering support, love, encouragement  
and prays of day and night during the past four years of my doctoral journey.

Thanks Mama Abah

for always believing in me and for encouraging me to strive my dreams

Thanks my dear lovely husband

caused always cheered me on when I was discouraged,  
wiped my tears away when the great research catastrophes stuck and he has most  
importantly been 100% confident in my ability this get this done.

Along with all hard working and respected lectures and friends.

Thank you very much and love you all.

## ACKNOWLEDGEMENT

First and foremost, I would like to express my sincere gratitude to my principal supervisor, Ts. Dr. Shahiron Shahidan for his continuous support throughout my PhD journey and research, and for his patience, motivation, enthusiasm and immense knowledge. His guide and wisdom has been a great help throughout my research process and thesis writing. I could not imagine having any better advisor and mentor for my PhD journey.

I would also like to thank my core supervisor, Prof. Madya Dr. Norazura Mohamad Bunnori and Dr. Noorwirdawati Ali for their encouragement, commitment and comments to improve my research and for their professional views. Cooperation and support from FKAAS and CGS administrative staffs are also highly appreciated.

I am deeply grateful to Universiti Tun Hussein Onn Malaysia (UTHM) for award me graduate research grant under Vot U448. Also to Ministry of Higher Education, Malaysia (MyBrain15) for sponsoring my PhD study and also for awarding my supervisor with the Fundamental Research Grant Scheme (FRGS) Vot 1576. Appreciation and thanks are also dedicated to the Academic and General staffs in laboratory especially to Mr. Suhaimi Harun, Mr. Amran Abd Rahman and Mr. Osman Abd Rahman for their support and cooperation during my study period.

Thanks are extended to my fellow mates during my PhD journey; Alif Syazani Leman, Mohamad Syamir Senin, Afif Iman, Norsarwani Mat Saman and many for the stimulating discussion and their willingness to share their knowledge throughout these years of study.

Finally, I would like to acknowledge for the love, support and constant encouragement that I receive from my family, my parents and siblings, my husband Ahmad Fattah Al-Islam, and last but surely not the least, my son Ahmad Izz Naufal and Ahmad Daiyan Wafiy who have never failed to brighten up my day.

## ABSTRACT

The development of new technology and rapid development in many countries have led to various types of pollution, especially acoustic pollution in urban areas. Furthermore, the huge production of Coal Bottom Ash (CBA) is treated as waste and often placed into impoundment ponds, silos or landfills, which has contributed to environmental issues. Usage of CBA in concrete production in reducing railway noise pollution reduce the environmental pollution. This study presents the acoustic and non-acoustic performance for a new concrete product that consists mainly of CBA. Grade 30 MPa concrete was cast with varying replacement percentages (0% to 100%) of CBA as fine aggregate replacement in concrete mixture. The specimens were cured for periods of 7, 28 and 90 days. The non-acoustic performance of CBA concrete demonstrated similar or even better performance than normal concrete by conducting compressive strength, splitting tensile strength, water absorption, water permeability and ultrasonic pulse velocity. The increase in CBA percentage in the concrete mixture has affected the compressive strength and splitting tensile strength of the sample which were lower than that of control concrete. CBA concrete can be recommended as good concrete due to its absorption properties. Based on the sound test conducted according to ISO 11654: 1997, it was found that CBA concrete can be classified as Class D (absorption). Class D materials are able to absorb more than 30% of sound by conducting impedance tube and reverberation time. In addition, the Noise Reduction Coefficient (NRC) performance for CBA concrete addresses more than 35% of the absorbed railway sound. CBA concrete showed an improvement in acoustic properties compared to normal concrete as it is able to reduce up to 3.74 dB of the existing railway noise level while normal concrete can only reduce up to 1.94 dB of the existing noise level.

## ABSTRAK

Pembangunan negara yang semakin maju dan canggih dengan teknologi baru telah mendatangkan pelbagai jenis pencemaran antaranya pencemaran bunyi hingar terutamanya di sekitar kawasan bandar. Selain itu, pengeluaran sisa arang batu iaitu abu arang bawah (CBA) yang semakin membimbangkan yang telah dihasilkan dianggap sebagai sisa dan sering dibuang di dalam kolam timbunan, silo atau tapak pelupusan yang telah menyumbang kepada isu-isu alam sekitar. Penggunaan CBA dalam penghasilan konkrit bagi mengurang pencemaran bunyi kereta api mampu mengurangkan pencemaran alam sekitar. Kajian ini dilakukan untuk mengkaji prestasi akustik dan bukan akustik bagi konkrit yang dihasilkan daripada campuran sisa arang batu. Campuran konkrit bergred 30 MPa dihasilkan dengan pelbagai variasi peratusan penggantian (0% sehingga 100%) dari CBA sebagai pengganti kepada agregat halus (pasir) di dalam campuran konkrit. Spesimen tersebut telah diawet selama 7, 28 dan 90 hari. Berdasarkan ujian yang telah dilakukan ianya mendapati bahawa prestasi konkrit campuran adalah sama atau lebih baik daripada konkrit biasa dengan melakukan ujian kekuatan mampatan, kekuatan tegangan, peyerapan air, kebolehtelapan air dan halaju nadi ultrasonik. Peningkatan jumlah peratusan CBA dalam campuran konkrit telah mempengaruhi kekuatan mampatan dan kekuatan tegangan yang lebih rendah daripada konkrit biasa. Selain itu, kadar serapan air dan penyusupan air bagi konkrit campuran CBA adalah lebih tinggi daripada konkrit biasa. Kadar serapan air bagi konkrit CBA meningkat apabila peratusan penggunaan CBA di dalam konkrit meningkat. Hasil ujian bunyi yang dilakukan terhadap konkrit campuran CBA mendapati nilai serapan bunyi adalah di kelas D (ISO 11654:1997). Selain itu juga, prestasi pekali pengurangan bunyi (NRC) bagi konkrit campuran CBA menunjukkan lebih daripada 35% bunyi diserap. Ianya juga telah menunjukkan potensi yang baik dari konkrit biasa iaitu kemampuannya untuk mengurangkan kadar bunyi keretapi sebanyak 3.74 dB berbanding konkrit biasa 1.94 dB.

## CONTENTS

<b>DECLARATION OF THESIS STATUS</b>	<b>i</b>
<b>EXAMINERS' DECLARATION</b>	<b>ii</b>
<b>TITLE</b>	<b>iii</b>
<b>STUDENT'S DECLARATION</b>	<b>iv</b>
<b>DEDICATION</b>	<b>v</b>
<b>ACKNOWLEDGMENT</b>	<b>vi</b>
<b>ABSTRACT</b>	<b>vii</b>
<b>ABSTRAK</b>	<b>viii</b>
<b>CONTENTS</b>	<b>ixx</b>
<b>LIST OF TABLE</b>	<b>xiv</b>
<b>LIST OF FIGURE</b>	<b>xvii</b>
<b>LIST OF SYMBOLS AND ABBREVIATIONS</b>	<b>xx</b>
<b>LIST OF APPENDICES</b>	<b>xxii</b>
<b>CHAPTER 1 INTRODUCTION</b>	<b>1</b>
1.1 Background of the study	1
1.2 Problem statement	4
1.3 Objective of the study	6
1.4 Scope of the study	7
1.5 Significant of the study	8
1.6 Thesis outline	9
<b>CHAPTER 2 LITERATURE REVIEW</b>	<b>10</b>
2.1 Introduction	10
2.2 Waste material	11
2.2.1 The use of commercial waste in concrete production	12
2.2.2 Industrial waste	16

2.3	Coal bottom ash	18
2.3.1	Disposal and usage of coal bottom ash	19
2.3.2	Coal bottom ash in concrete production	21
2.4	Physical properties of coal bottom ash	25
2.4.1	Particle size	25
2.4.2	Fineness modulus	25
2.4.3	Specific gravity	26
2.4.4	Chemical composition	27
2.5	Properties of fresh coal bottom ash concrete	28
2.6	Properties of hardened coal bottom ash concrete	29
2.6.1	Density	29
2.6.2	Compressive strength	30
2.6.3	Splitting tensile strength	31
2.6.4	Water absorption	32
2.7	Previous study on the usage of coal bottom ash	33
2.8	Noise pollution	37
2.8.1	Railway noise and related factor	39
2.8.2	Railway system issues in Malaysia	43
2.9	Noise reduction device	45
2.9.1	Noise barriers as sound absorber	46
2.10	Summary	51
<b>CHAPTER 3</b>	<b>METHODOLOGY</b>	<b>53</b>
3.1	Introduction	53
3.2	Research flow	55
3.3	Noise monitoring	55
3.3.1	Selection of study area	55
3.3.2	Data collection and equipment selection	57
3.4	Preparation of raw materials for concrete specimens	60
3.4.1	Water	61
3.4.2	Portland cement	61
3.4.3	Aggregates	61
3.4.4	Coal Bottom Ash	62

3.5	Material characterisation testing	65
3.5.1	Sieve analysis	65
3.5.2	Specific gravity	66
3.5.3	Bulk density	68
3.5.4	Chemical and microstructural characterisation	68
3.6	Design calculation for CBA concrete	70
3.7	Preparations of concrete specimen	71
3.8	Non acoustic performance testing	73
3.8.1	Workability	74
3.8.2	Density of hardened concrete	75
3.8.3	Compressive strength	75
3.8.4	Splitting tensile strength	76
3.8.5	Water absorption	77
3.8.6	Water permeability	78
3.8.7	Ultrasonic pulse velocity	80
3.9	Acoustic performance testing	81
3.9.1	Impedance tube	81
3.9.2	Reverberation time	84
3.9.3	Sound absorption coefficient (SAC) and Noise reduction coefficients (NRC)	88
3.10	Summary	89
<b>CHAPTER 4</b>	<b>NOISE LEVEL IDENTIFICATION</b>	<b>90</b>
4.1	Introduction	90
4.2	Determination of noise level	90
4.2.1	Different locations	90
4.2.2	Day versus Night	98
4.2.3	Different types of trains	100
4.3	Summary	102



<b>CHAPTER 5</b>	<b>PROPERTIES OF CONCRETE INCORPORATING CBA AS FINE AGGREGATE REPLACEMENT</b>	<b>103</b>
5.1	Introduction	103
5.2	Characteristic of aggregate and CBA	104
5.2.1	Sieve analysis	104
5.2.2	Specific gravity	108
5.2.3	Bulk density	112
5.2.4	Chemical composition	113
5.2.5	Summary characterisation of materials	116
5.3	Properties of fresh concrete	117
5.4	Hardened concrete properties	120
5.4.1	Dry density	120
5.4.2	Compressive strength	123
5.4.3	Splitting tensile strength	126
5.4.4	Water absorption	130
5.4.5	Water permeability	133
5.4.6	Ultrasonic pulse velocity	138
5.5	Summary	141
<b>CHAPTER 6</b>	<b>ACOUSTIC PROPERTIES OF CBA CONCRETE</b>	<b>144</b>
6.1	Introduction	144
6.2	Impedance tube test	144
6.3	Reverberation room test	153
6.4	Prediction or reduction railway noise (Decibel drop)	160
6.5	Summary	163
<b>CHAPTER 7</b>	<b>CONCLUSION AND RECOMMENDATION FOR FUTURE WORK</b>	<b>164</b>
7.1	Introduction	164
7.2	Conclusion	164
7.2.1	Determination railway noise level	164
7.2.2	Non-acoustic performance of coal bottom ash concrete	165
7.2.3	Acoustic performance of coal bottom ash concrete	167

## 7.3 Recommendation for future work

168

**REFERENCES****170****APPENDIX A****APPENDIX B****APPENDIX C****APPENDIX D**

## LIST OF TABLE

2.1	Previous research studies on the type of waste material in concrete production	12
2.2	Previous research studies on the usage of coal bottom ash in construction industry	21
2.3	Previous research studies on the usage of coal bottom ash in concrete production	22
2.4	Fineness modulus of coal bottom ash based on previous study	26
2.5	Specific gravity of coal bottom ash based on previous study	27
2.6	Chemical composition of coal bottom ash at different power plant station	27
2.7	Workability of coal bottom ash concrete	28
2.8	Density of coal bottom ash concrete	29
2.9	Compressive strength of coal bottom ash concrete at 28 days of curing age	30
2.10	Splitting tensile strength of coal bottom ash concrete	32
2.11	Water absorption of coal bottom ash concrete	33
2.12	Previous research on the utilization of coal bottom ash fine aggregate in concrete production	34
2.13	Comparative sound level	37
2.14	Previous study on the transportation noise	38
2.15	Types of railway noise	40
2.16	Issue related to the railway system in Malaysia based on previous research	44
2.17	Limiting sound level for railways in Malaysia	45

2.18	Active and Passive ways for reducing noise	46
2.19	Previous study on the types of material used as sound absorptive material	50
3.1	Mix design per m <sup>3</sup> of normal concrete	70
3.2	Concrete mix design for each percentage of CBA as fine aggregate replacement for 1m <sup>3</sup> of concrete	71
3.3	Specimen sizes used in this research	72
3.4	Number of sample for each test	72
4.1	Limiting sound level for railways in Malaysia	91
4.2	Maximum and minimum noise level recorded at different railway stations	96
4.3	Maximum and minimum noise level recorded at different railway station (day and night)	99
4.4	Percentage difference of noise level produced by different type trains.	100
5.1	Sieve analysis of fine aggregate	104
5.2	Sieve analysis of CBA	105
5.3	Fineness modulus of CBA reported by previous researchers	107
5.4	Percentage difference for Fineness Modulus of CBA between obtained from the present study and those reported in standard and previous researchers	107
5.5	Comparison between specific gravity values of CBA obtained from the present study and the one reported in previous researcher	109
5.6	Percentage difference specific gravity values of CBA obtained from the present study and those reported by previous researchers	110
5.7	Density of CBA and fine aggregate obtained from the present study and those reported by previous researches	112
5.8	Chemical composition of fine aggregate and CBA obtained from different power plant stations	114

5.9	Physical properties of sand and coal bottom ash	116
5.10	Hardened density of coal bottom ash concrete at 7, 28 and 90 days	121
5.11	Compressive strength of CBAC at 7, 28 and 90 days.	123
5.12	Splitting tensile strength of CBAC at 7, 28 and 90 days.	126
5.13	Percentage difference of splitting tensile strength with compressive strength of coal bottom ash concrete	129
5.14	Water absorption of CBAC	130
5.15	Water permeability of CBAC	134
5.16	Ultrasonic pulse velocity of CBAC as replacement of fine aggregate in concrete	138
5.17	Concrete quality grading as per BS 1881:1983	140
6.1	Sound absorption coefficient for CBA concrete at low frequency range	145
6.2	Sound absorption coefficient for CBA concrete at high frequency range	146
6.3	NRC performance of CBA concrete	149
6.4	Density, strength and NRC value for CBA concrete	150
6.5	Sound absorption coefficient comparison between CBA concrete mixtures with non-CBA concrete mixture	153
6.6	Sound absorption coefficient for CBAC acoustic panels	158
6.7	Rating of sound absorption for CBAC acoustic panels according to ISO 11654 :1997	160
6.8	Decibel drop of railway noise level at each station	162

## LIST OF FIGURE

1.1	Location of coal-fired power plants in Malaysia	3
2.1	Production of coal ash at coal fired thermal power plant	17
2.2	Tanjung Bin Power Plant Station	19
2.3	Ash pond	20
2.4	Railways noise type	40
2.5	Level of railway noise and their associated speed dependency	42
2.6	Alteration of noise paths using a noise barriers	47
2.7	Reflection, absorption and transmission of sound	48
2.8	Viscous drag mechanism of absorption in porous material	49
3.1	Research flow chart	54
3.2	KTM route map in Malaysia	56
3.3	(a) Locomotive intercity diesel train, (b) Electric Train Service (ETS) that operated in the study area.	57
3.4	Sound Level Meter (SLM) device used in the research	58
3.5	SLM positioned near Electric Train Services (ETS) at Gemas Station.	59
3.6	(a) SLM positioned near a locomotive train diesel engine (b) SLM positioned near the pantograph of the ETS	60
3.7	Coal Bottom Ash (CBA)	62
3.8	Location of Tanjung Bin Power Plant Station	63
3.9	Material preparation for CBA before it is used in concrete mixture	64
3.10	Mechanical shaker	66
3.11	Process involved in the specific gravity test	67
3.12	SEM and XRF Machine	69

3.13	The curing process of concrete specimens	73
3.14	Slump testing	74
3.15	Compressive strength testing.	76
3.16	Tensile splitting strength test setup	77
3.17	Processes involved in the water absorption test	78
3.18	Water permeability testing	80
3.19	100 mm concrete sample for impedance tube testing	82
3.20	(a) Impedance tube machine	83
	(b) Calibration process of microphone	
	(c) Impedance tube test in progress	
3.21	Specimens arrangement in the mini chamber	85
3.22	All the perimeter surface area of specimen were sealed with reflective material	85
3.23	Schematic drawing and microphone positions.	86
3.24	(a) CBA concrete sample inside the mini chamber	87
	(b) signal analyzer	
4.1	(a) Noise level recorded at Kluang station	92
	(b) Noise level recorded at Segamat station	93
4.2	(a) Noise level recorded at Gemas station	94
	(a) Noise level recorded at Kuala Lumpur station	95
4.3	Kuala Lumpur Railway station with enclosure structure	97
4.4	Location of study area; (a) Kluang railway station, (b) Segamat railway station and (c) Gemas railway station	98
4.5	Type of train operates in the selected area of study; (a) Locomotive Diesel Train/ Freight Train, (b) KTM commuter and (c) ETS.	101
5.1	Sieve analysis for sand and CBA	106
5.2	Specific gravity testing; (a) sand and (b) CBA	109
5.3	Vesicular texture of coal bottom ash	111
5.4	Relationship between slump and concrete containing different percentage of CBA	117
5.5	Density of CBA concrete at different percentage	122

5.6	Compressive strength versus curing days	124
5.7	Splitting tensile strength versus percentage replacement at all curing age.	127
5.8	Water absorption CBA concrete versus percentage of CBA	131
5.9	Relationship between water absorption and compressive strength of CBA concrete at 28 days of curing age	132
5.10	Water permeability with curing age of CBA concrete	135
5.11	Particle image at 500x magnification of (a) fine aggregate and (b) CBA	136
5.12	Relationship between permeability coefficients and water absorption of CBA concrete.	137
5.13	Variation of pulse velocity with curing age	140
6.1	Comparison of sound absorption coefficient with different percentage of CBA (low and high frequency)	147
6.2	Relationship between NRC value and hardened density of CBA concrete.	151
6.3	Relationship between NRC value and compressive strength of CBA concrete.	152
6.4	RT mini chamber	154
6.5	Reverberation time for an empty chamber and chamber occupied with CBAC acoustic panels	155
6.6	Sound absorption performance of CBAC acoustic panels in the reverberation chamber	157
6.7	Rating curves for CBAC acoustic panels	159



## LIST OF SYMBOLS AND ABBREVIATIONS

dB	-	Decibel
dBA	-	A weighted decibels
Am	-	Ante meridiem (Before noon)
Pm	-	Post meridiem (After noon)
kPa	-	Kilo pascal
Pa	-	Pascal
$\alpha$	-	Sound absorption coefficient
$\alpha_{pi}$	-	Arithmetic mean value of sound absorption coefficient
$\alpha_w$	-	Weighted absorption coefficient
$\alpha_s$	-	Sabine's absorption coefficient
m	-	Meter
mm	-	Millimeter
kg	-	Kilogram
S	-	Second
W	-	Watt
MW	-	MegaWatt
GW	-	GigaWatt
%	-	Percent
Hz	-	Hertz
ACAA	-	American Coal Ash Association
ASTM	-	American Society for Testing and Materials
BS	-	British Standard
CBA	-	Coal Bottom Ash
CBAC	-	Coal Bottom Ash Concrete
CO <sub>2</sub>	-	Carbon dioxide
DOE	-	Department of Environment
EHS	-	Environmentally Hazardous Substance
EN	-	European Norm
EQA	-	Environment Quality Act

ERL	-	Expres Rail Line
ETS	-	Electric Train Service
FBA	-	Fine Bottom Ash
FGD	-	Fuel Gas Desulphurization
IPP	-	Independent Power Producers
ISO	-	International Standards Organization
KTMB	-	Keretapi Tanah Melayu Berhad
MPa	-	Mega Pascal
MRT	-	Mass Rapid Transit
MSW	-	Municipal Solid Waste
NRC	-	Noise Reduction Coeffieicent
NRDs	-	Noise Reduction Device
PCC	-	Portland Cement Concrete
RHA	-	Rice Husk Ash
RT	-	Reverberation Time
SAC	-	Sound Absorption Coefficient
SCC	-	Sel- compacting concrete
SEM	-	Scanning Electron Microscopy
SF	-	Silica Fume
SLM	-	Sound Level Meter
SPAD	-	Suruhanjaya Pengangkutan Awam Darat
SW	-	Schedule Waste
TNB	-	Tenaga Nasional Berhad
UPV	-	Ultrasonic Pulse Velocity
WBA	-	Washed Bottom Ash
XRF	-	X-Ray Fluorescent

## **CHAPTER 1**

### **INTRODUCTION**

#### **1.1 Background of the study**

Noise is one of the most negative impacts of transport affecting the quality of the environment. It affects a large number of people as it often causes annoyance and irritation which affect various human activities. Noise pollution from the transportation sector can interfere with the environment. Even though railways are one of the most environmentally friendly types of transportation due to its energy efficiency and emittance of less hazardous substances, railway noise produced by freight trains, speed trains and high-speed trains remains a major environmental issue. The investigation of railway noise is getting more attention among researchers as it is continuously reviewed from year to year starting from 2010 to 2019.

In Malaysia, a handful of studies are limited to surveys of railway noise status and its influence on the community. However, various techniques can be employed to reduce railway noise at source including dampers, sleepers, barriers, tunnels and so on. A noise barrier wall is one of the most economic and innovative methods for reducing noise. Many industries have come out with many types of noise barriers which can be built out of wood, concrete, masonry, metal and transparent materials. It also comes in various shapes such as hollow blocks or panels. However, based on previous research, noise barriers made of recycled aggregate, recycled rubber, recycled ceramic industry waste and other types of waste have also been invented.

Waste has long been a major issue for the environment, the society and the economy (Arenas *et al.*, 2015). Industrial waste poses a potential serious hazard to the environment as most industrial processes employ chemicals or chemically produced materials (Aja *et al.*, 2016). In Malaysia, the manufacturing sector was first identified as generators of toxic and hazardous waste which is an environmental hazard for living things. Due to rapid development, the quantity of solid waste generated every year continues to increase. The quantity of solid waste in Malaysia is projected to increase from 19,100 tonnes per day in 2005 to 30,000 tonnes per day by 2020 with the annual population growth rate 2.5 per cent (Ali *et al.*, 2018)

One of the manufacturing activities that contribute to the generation of industrial waste is electricity power generation. Due to the increasing demand for electricity every year, several coal fired thermal power plants have been set up in large numbers in the country to meet consumer demand (Singh & Siddique, 2013).

There are several coal power plants located in Malaysia namely Tanjung Bin, Jimah, Sultan Salahuddin Abdul Aziz/Kapar and Sultan Azlan Shah/Manjung coal power plant stations as shown in Figure 1.1. Most of these power plants have been using coal as the main source for generating electricity. This, in turn, produces large volumes of coal ash (Oh *et al.*, 2010). Fly ash, coal bottom ash (CBA), boiler slag and Flue Gas Desulphurisation (FGD) sludge are wastes produced during the combustion process in coal-fired power plants. According to Kockwood & Evans (2012), coal ash is a hazardous waste where the toxic remains of coal burning in power plants are full of chemicals that cause cancer, developmental disorders and reproductive problems. Coal bottom ash (CBA) is still being treated as solid waste material which is disposed of on open land and is not used in any form (Singh & Siddique, 2015).

The massive quantity of CBA produced from the coal combustion process for electricity generation poses a risk to human health and the environment. CBA can contaminate ground or surface water and subsequently poison living organisms. Therefore, CBA is gradually being incorporated in the construction industry as road base layers, pavements, structural fill, drainage media, aggregate for concrete and also in manufactured soil products to reduce environmental pollution (Kuo, Poon & Etxeberria, 2013). In previous research, CBA has been used as a partial replacement

of natural aggregates (fine aggregate or coarse aggregate). It possesses high fire resistance due to its wide evaporation plateau (Abubakar *et al.*, 2012a).




Figure 1.1: Location of coal-fired power plants in Malaysia (Edited from Muhardi *et al.*, 2010)

This research mainly studies the potential application of CBA in concrete which can hopefully be used as absorptive material in railway noise barriers. The usage of CBA as an absorbent material in concrete mixture has demonstrated similar properties to other conventional materials used for sound absorbing applications (Arenas *et al.*, 2013). Besides that, the findings of this study may also help reduce noise pollution which poses a risk to both humans and the environment.

## 1.2 Problem Statement

Coal is the main source used for the generation of electricity worldwide. According to Muhandi *et al.*, (2010), it has been recognised as an important source of fuel in Malaysia. The demand for coal for electricity generation increased sharply from an estimated 6.03 million tonnes in 2000 to between 19 to 20 million tonnes per annum by 2010 (Mohamed & Teong, 2010). It is also expected to increase by more than 30 million tonnes per annum by 2020. Coal remains one of the main sources for energy generation due to its low price and it being the most abundantly available fossil fuel in Malaysia (Suruhanjaya Tenaga, 2018).

CBA is one of the non-combustible materials that is produced after the coal combustion process for electricity generation. CBA is the coarser part which is collected at the bottom of the coal furnace. It consists of angular ash particles which are too heavy and large to be carried up into smoke stacks. Typically, CBA is simply disposed of on open land after the burning process. Due to coal combustion, an increased volume of CBA is continually being disposed of on land. The volume of CBA that is being disposed of is increasing by the year. According to the Department of Environment (DOE) Malaysia, 364,425.95 MT/year of coal ash was generated in 2010 while the total quantity of coal ash generated is 342,560.39 MT/year in 2011. This represents an increase of 6% in coal ash production in 2011. Meanwhile, in Tanjung Bin power plant has produced 50,000 metric tonnes of coal ash (fly and bottom ash) every month (Abdullah *et al.*, 2018).

Due to the huge amount disposal of CBA has contributed to environmental pollution such as the pollution of Emory and Clinch Rivers in Kingston, Tennessee. This also happened to Tanjung Bin power plant which is required large area for disposal storage of CBA (Abdullah *et al.*, 2018). The disposal of CBA have its disadvantages in the sense when the pond site is not lined with concrete has cause the heavy metals tends to leach into natural ground water and contamination to the environmental (Abubakar *et al.*, 2012). According to Gottlieb *et al.*, (2010), the water in the rivers contained heavy metals such as arsenic and elevated levels of other toxic metals such as lead, thallium, barium, cadmium, chromium, mercury and nickel. In

## LIST OF APPENDIX

- A Supportive document/Letter
- B Concrete mix design
- C Experimental data
- D List of publication



Malaysia, CBA is classified as Scheduled Waste SW 104 (Environmental Quality Act) and hazardous waste due to its toxicity.

On the other side, increase in human population and daily activities has caused traffic congestion, which is nowadays the biggest issue faced by road users. However, the Malaysian government has begun to gradually overcome the issues by providing more railways service in Malaysia. The railway services provided by the government help ease the public's movement in both urban and rural areas (Khalid *et al.*, 2014).

The demand for usage of trains among the public faces several challenging issues such as noise and vibration issues in residential areas as reported in Sinar Harian on 28 April 2016. According to the article, residents of Sri Teratai Apartment in Puchong Jaya claimed that noise from railway services has affected their daily activities. They had difficulty sleeping. Babies and the elderly were especially disturbed by the noise generated by trains. This also be supported by Fawwaz *et al.*, (2013) where found the residents that lived nearby LRT station Taman Melati also faced the same problem which is difficulties to sleep early due to the noise from LRT line which is close to their neighbourhood.

According to Shahidan *et al.*, (2017) most of measured noise levels of railways reached more than 90 dB which exceeds the permissible noise limit set by the Department of Environment (DOE) Malaysia. The noise limits for day and night are 60 dB and 50 dB respectively for noise sensitive areas or low density residential areas.

Considering the increase in noise emissions from railway services in residential areas, environmentally friendly materials is needed. For example, coconut shell powder and rubber ash as well as other waste products have been used in the construction industry especially in concrete production. Therefore, based on the issue highlighted, this study has selected CBA as absorptive material in reducing noise pollution. CBA is considered as a waste product which pollutes the environment.

CBA have been used in concrete production as cement replacement and fine aggregate replacement previous researchers. It has the potential to be used in concrete mixes. Most of researches used CBA to improve the mechanical properties of concrete such strength development and durability of the concrete since the findings shows the similar pattern with the normal concrete. Eventhough, there were research had been conducted by using CBA with different layer in the concrete production to improve



## REFERENCES

- Abubakar, A. U. and K. S. Baharudin (2012a). "Potential Use of Malaysian Thermal Power Plants". *International Journal of Sustainable Construction Engineering and Technology*, 3(2), 25–37.
- Abubakar, A. U. and K. S. Baharudin (2012b). "Properties of concrete using Tanjung Bin power plant coal bottom ash and fly ash". *International Journal of Sustainable Construction Engineering and Technology*, 3(2), 56–69.
- Abubakar, A. U. and K. S. Baharudin (2013c). "Tanjung Bin Coal Bottom Ash: From Waste to Concrete Material". *Advanced Materials Research*, 705(June), 163–168.
- Adelman-Larsen, N. W., , E. R. Thompson and A. C. Gade (2010). "Suitable reverberation times for halls for rock and pop music".
- Administration, F. R. (2004). "Use of Locomotive Horns at Highway-Rail Grade Crossing". *Department of Transportation*, 1–58.
- Aggarwal, P., Y. Aggarwal and S. M. Gupta, (2007). "Effect of Bottom Ash As Replacement of Fine". *Asian Journal of Civil Engineering (Building and Housing)* Vol., 8(1), 49–62.
- Ahmad Maliki, A. I. F., S. Shahidan, N. Ali, N. I. R. Ramzi Hannan, S. S Mohd Zuki, M. H. W. Ibrahim and M. Abdul Rahim,. (2017). Compressive and tensile strength for concrete containing coal bottom ash. *IOP Conference Series: Materials Science and Engineering*, 271, 012055.
- Aja, O. C., H. H. Al-Kayiem, M. G. Zewge and M. S. Joo (2016). "Overview of Hazardous Waste Management Status in Malaysia". *Management of Hazardous Wastes*.
- Ajagbe, W. O., M. A. Tijani, I. S. Arohunfegbe and M. T. Akinleye (2018). "Assessment of Fine Aggregates from Different Sources in Ibadan and Environs for Concrete Production". *Nigerian Journal of Technology Development*, 15, 7–13.
- Akinayo, O., Ayandokun, A., and Okah-avae, O. u. (2007). "Propagation of sound: Its tavel path, travel medium and behavior in the mediums". *Bachelor theses, Federal University of Technology Akure, Ondo State*.

- AL-Rahman, L. A., R. I Raja, and R. A. Rahman, R. A (2012). "Attenuation of noise by using absorption materials and barriers: a review". *International Journal of Engineering and Technology*, 2(7), 1207–1217.
- Al-Zubaid, A. B., I. Ali, K. Muttar, A. Pina, P. Ferrão, and A. I Andri (2017). "The Effect of Recycled Glass Mechanical Properties Concrete of Green Concrete Assessing the feasibility using the heat temper". *Energy Procedia*, 119, 680–692.
- Aletta, F., M. Masullo and L. Maffei (2011) "Annoyance and pleasantness assessment for railways noise barriers by means of immersive virtual reality".
- Ali, S., M. H. W. Ibrahim, N. Jamaluddin, N., and M. Fadzil (2018). "Performance of concrete containing coal bottom ash with different fineness as a supplementary cementitious material exposed to seawater". *Engineering Science and Technology, an International Journal*.
- Ali, S. A. (2011). Industrial noise levels and annoyance in Egypt. *Applied Acoustics*, 72(4), 221–225.
- Alkaabi, K. A. (2017). "Studying the effects of aircraft noise around abu dhabi international airport, uae on the surrounding residential and work places" *Civil Engineering and Urban Planning: An International Journal*, 4(2).
- Alqahtani, F. K., M. I Khan, G. Ghataora and S. Dirar (2017). "Production of recycled plastic aggregates and its utilization in concrete". *Journal of Materials in Civil Engineering*, 29(4), 04016248.
- Amares, S. (2017). "A Review : Characteristics of noise absorption material". *Journal of Physics Conference*.
- Amares, S., Sujatmika, E., Hong, T. W., Durairaj, R. and Hamid, H.S.H.B. (2017). A Review : Characteristics of Noise Absorption Material. *Journal of Physics Conference*.
- Anderson, C. B. (2009). "Assessment of railway activity and train noise exposure: a teaneck, new jersey, case study" .
- Andrade, L. B., J. C Rocha and M. Cheriaf (2007a). "Aspects of moisture kinetics of coal bottom ash in concrete". *Cement and Concrete Research*, 37(2), 231–241.
- Andrade, L. B., J. C Rocha and M. Cheriaf. (2007b). "Evaluation of concrete incorporating bottom ash as a natural aggregates replacement". *Waste Management*, 27(9), 1190–1199.
- Andrade, L. B., J. C Rocha and M. Cheriaf (2009). "Influence of coal bottom ash as fine aggregate on fresh properties of concrete". *Construction and Building Materials*, 23(2), 609–614.

- Arenas, C., C. Leiva, L. F. Vilches, and H. Cifuentes (2013). "Use of co-combustion bottom ash to design an acoustic absorbing material for highway noise barriers". *Waste Management*, 33(11), 2316–2321.
- Arenas, C., C. Leiva, L. F. Vilches, H. Cifuentes and M. Rodríguez-Galán (2015). "Technical specifications for highway noise barriers made of coal bottom ash-based sound absorbing concrete". *Construction and Building Materials*, 95, 585–591.
- Argiz, C. and A. Moragues (2018). "Use of ground coal bottom ash as cement constituent in concretes exposed to chloride environments", 170, 25–33.
- Arif, A. A. (2015). "Analysis on noise distribution at different monorail station in Kuala Lumpur".
- Arumugam, B. (2014). "Effect of specific gravity on aggregate varies the weight of concrete cube". *SSRG International Journal of Civil Engineering (SSRG-IJCE)*, 1(August), 1–9.
- ASTM C 33, Standard specification for concrete aggregates, United States, American Society of Testing Material.
- ASTM C 496, Standard specification test method for splitting tensile strength of cylindrical concrete specimens, United States, American Society of Testing Material.
- ASTM C 618, Standard specification for coal fly ash and raw or calcined natural pozzolan for use in concrete, United States, American Society of Testing Material.
- ASTM C 1602, Standard specification for mixing water used in the production of hydraulic cement concrete. United States, American Society of Testing Material.
- ASTM D 4254, Standard specification test methods for minimum index density and unit weight of soils and calculation of relative density, United States, American Society of Testing Material.
- Awoyera, P. O., J. M Ndambuki, J. O. Akinmusuru and D. O. Omole (2016). "Characterization of ceramic waste aggregate concrete". *HBRC Journal*, 282–287.
- Azalan, A., M. I Ghazali and N. Jafferri (2011). "An Investigation on factors that cause error in reverberation time measurement ( ISO 3382 ) in UTHM lecturer room", 1(Iso 3382), 4–9.
- Barron, M. (2009). "Auditorium acoustics and architectural design, (2nd edition)", 2009–2011.
- Bash, E. (2015). "Reducing Railway Noise Pollution". PhD Proposal.

- Basirun, N. F., M. W. H. Ibrahim, and N. Jamaludin (2017). "A Review : The effect of grinded coal bottom ash on concrete", 01007, 1–8.
- Bies, D. and C. Hansen, (2009). "Engineering Noise Control": Theory and practice (Vol. 3).
- Bistrup, M. L., S. Hygge, L. Keiding, and W. Passchier-Vermeer (2001). "Health effects of noise on children and perception of the risk of noise".
- Bjeli, M., M. Vuki, A. Petrovi and M. Pljaki (2012). "Analysis of materials used for production of noise protection barriers". 23rd National Conference and 4th International Conference Noise and Vibration, 10, 101–103.
- Bradshaw, S. (2011). "User guideline for coal bottom ash and boiler slag in green infrastructure construction".
- British Standard 882 (1992). British standard for testing concrete: Specification for aggregates from natural sources for concrete, British Standard Institution.
- British Standard 1097-6 (2000). British standard for testing mechanical and physical properties of aggregates: Determination of particle density and water absorption. British Standard Institution.
- British Standard 1377-2 (1990). British standard for soils for civil engineering purpose: Classification tests. British Standard Institution.
- British Standard 1881-102 (1983). British standard for testing concrete: Method for determination of slump British Standard Institution.
- British Standard 1881-122 (2011). British standard for testing concrete: Method for determination of water absorption, British Standard Institution.
- British Standard 1881-203 (1986). British standard for testing concrete: Recommendations for measurement of velocity of ultrasonic pulses in concrete, British Standard Institution.
- British Standard EN 12350-2 (2009). British standard for testing fresh concrete: Slump test, British Standard Institution.
- British Standard EN 12390-2 (2009). British standard for testing hardened concrete: Making and curing specimens for strength tests, British Standard Institution.
- British Standard EN 12390-3 (2009). British standard for testing hardened concrete: Compressive strength of test specimens, British Standard Institution.
- British Standard EN 12390-6 (2009). British standard for testing hardened concrete: Tensile splitting strength of test specimens, , British Standard Institution.
- British Standard EN 12390-7 (2009). British standard for testing hardened concrete: Density of hardened concrete, , British Standard Institution.

- British Standard EN 12390-8 (2009). British standard for testing hardened concrete: Depth of penetration of water under pressure, British Standard Institution.
- British Standard EN 12504-4 (2009). British Standard for testing hardened concrete: Determination of ultrasonic pulse velocity, British Standard Institution.
- British Standard EN 12620-2 (2013). British standard for aggregate concrete. British Standard Institution.
- British Standard EN 13055. British Standard for properties of Lightweight Aggregates
- British Standard EN ISO 140 (1998). British Standard for acoustics measurement of sound insulation in buildings and of building elements. Requirements for laboratory test facilities with suppressed flanking transmission, British Standard Institution.
- British Standard EN ISO 354 (2003). British Standard for acoustic measurement of sound absorption in a reverberation room, British Standard Institution.
- British Standard EN ISO 10534-1 (2001). British Standard for acoustic: Determination of sound absorption coefficient and impedance in impedances tubes. Method using standing wave ratio, British Standard Institution.
- British Standard EN ISO 11654 (1997). British Standard for acoustic measurement sound absorbers for use in buildings: rating of sound absorption, British Standard Institution.
- Bruce, W. R. and M. P. Tharaniyil. (2013). "Coal Combustion Products Utilization Handbook". (S. Jody and D. Waterstreet, Eds.) (third). We Energies.
- Brüel, and Kjær. (2007). "Product Data- PULSE Acoustic Material Testing in a Tube Type 7758".
- Bunn, F. and . P. H. TZannin, (2016). "Assessment of railway noise in an urban setting". Applied Acoustics, 104, 16–23.
- Cadersa, A. and I. Auckburally, (2014). "Use of unprocessed coal bottom ash as partial fine aggregate replacement in concrete". University of Mauritius Research Journal, 30, 62–84.
- Chandra, J., P. Putra, P. and I. Rahmaniar, I. (2018). "Evaluation of reverberation time of class room", 020042.
- Chen, Z., and R. C Maher (2004) "Atmospheric sound propagation considerations for the birdstrike project 1 a simple model for sound propagation".
- Cheng, A. (2012). "Effect of incinerator bottom ash properties on mechanical and pore size of blended cement mortars". Materials and Design, 36, 859–864.

- Chindaprasirt, P. C. Jaturapitakkul, W. Chalee and U. Rattanasak (2009). "Comparative study on the characteristics of fly ash and bottom ash geopolymers". *Waste Management*, 29(2), 539–543.
- Chowdhury, S., M. Mishra, and O. Suganya (2015). "The incorporation of wood waste ash as a partial cement replacement material for making structural grade concrete: An overview". *Ain Shams Engineering Journal*, 6(2), 429–437.
- CivilToday (2019). Retrieved April 3, 2019, <http://civiltoday.com>.
- Clairbois, J., and M. Garai (2015). "The European standards for roads and railways noise barriers : state of the art 2015", (May 2015), 45–50.
- Clark, C., and S. A. Stansfeld (2007). "The Effect of Transportation Noise on Health and Cognitive Development : A Review of Recent Evidence".
- Comision, E., and D. G Energy, (2007). "Assessment Study on Rail Noise Abatement Measures". *Evaluation*, 1–129.
- De la Colina Martínez, A. L., Martínez Barrera, G., Barrera Díaz, C. E., Ávila Córdoba, L. I., Ureña Núñez, F., and Delgado Hernández, D. J. (2019). Recycled polycarbonate from electronic waste and its use in concrete: Effect of irradiation. *Construction and Building Materials*, 201, 778–785.
- Demir, G., Kablan, A., Avşar, Y., Alyüz, Ü., Ökten, H. E., and Yalçın, Ş. (2016). Railway Noise Pollution Prevention in Terms of Regulations: Case Study of Istanbul. *International Journal of Environmental Science and Development*, 7(3), 198–202.
- Demir, I. (2006). An investigation on the production of construction brick with processed waste tea. *Build Environ*;41:1274–8.
- Deparment of Environment, M. of N. R. and E. M. (2007). *The Planning Guidelines for Environmental Noise Limits and Control* (2nd editio).
- Devinder Singh. (2016). Study on the performance of concrete using sugarcane bagasse ash and coal bottom ash.
- Diana, N., and Mahudin, M. (2018). Preliminary Assessment and Prioritisation of Demand Management Strategies for Reducing Train Overcrowding. *Social Sciences and Humanities*, 26(1), 491–506.
- DOE. (1974). Environmental quality act, 1974 (act 127) arrangement of sections, 1974(Act 127).
- Dragonetti, R., Lanniello, C. and Romano, R. A (2009), Reverberation time measurement by the product of two room impulse responses, *Applied Acoustic*, 70 (1), 231 - 243.



- DuPont. (2009). Acoustic : Different kinds of materials for traffic noise barriers. Urban Acoustic.
- Ernida, N., Abidin, Z., Haziman, M., and Ibrahim, W. (2014). The Effect of Bottom Ash on Fresh Characteristic , Compressive Strength and Water Absorption of Self-Compacting Concrete, (October).
- European Environment Agency (2010), Environment and Health: Noise.
- Evangelista, L., and de Brito, J. (2010). Durability performance of concrete made with fine recycled concrete aggregates. *Cement and Concrete Composites*, 29(5), 397–401.
- Evangelista, L., Guedes, M., de Brito, J., Ferro, a. C., and Pereira, M. F. (2015). Physical, chemical and mineralogical properties of fine recycled aggregates made from concrete waste. *Construction and Building Materials*, 86, 178–188.
- Everest, F. A and Pohlmann, K. C, *Master Handbook of Acoustics*, 5th ed, Mc Graw Hill, pp 164-165, 193-197, 2009
- Faisal, S. ., Mazenan, P. ., Shahidan, S., and Irwan, J. . (2018). Review of coal bottom ash and coconut shell in the production of concrete. *IOP Conference Series: Materials Science and Engineering* paper.
- Fawwaz, A., Ahmad, B., Pollution, N., Study, C., and Melati, T. (2013). Noise Pollution, Case Study : Taman Melati.
- Federal Railroad Administration Office of Safety Analysis: Regulatory Evaluation and regulatory flexibility assessment for use of locomotive horns at highway-rail grade crossings final rule, July 21, 2003.
- Fernandez, P., Diez, I., Eguiguren, J. L., and Aspuru, I. (2013). Noise barriers customized to abate non conventional noise sources, (SEPTEMBER), 1–8.
- Florentina, F. (2008). Road Traffic Noise: A study of Skåne region , Sweden.
- Floyd, R. W. (2007). The Absorption of Sound By Materials: A Method of Measurement with Results for Some Materials.
- Franklin. *Pollution in the UK*, Sweet& Maxwell. London. 1995
- Foraster, M., Eze, I. C., Vienneau, D., Schaffner, E., Jeong, A., Héritier, H., ... Röösli, M. (2018). Long-term exposure to transportation noise and its association with adiposity markers and development of obesity, 121(June), 879–889.
- Ghafoori, N. and Bucholc, J. (1997). Properties of high calcium dry bottom ash concrete. *ACI Materials Journal* 94 (2), 90-101.

- Ghosh, A., Ghosh, A., and Neogi, S. (2018). Reuse of fly ash and bottom ash in mortars with improved thermal conductivity performance for buildings. *Heliyon*, 4(11).
- GoogleMaps (2019). Retrieved April 3, 2019, <http://googlemaps.com/> Tanjung bin power plant.
- Goran M. A (2015), Permeability of concrete, Kurdistan Engineers Union, June.
- Gottlieb, B., Gilbert, S., and Gollin Evans, L. (2010). Coal Ash: The toxic threat to our health and environment.
- Gu, L., and Ozbakkaloglu, T. (2016). Use of recycled plastics in concrete: A critical review. *Waste Management*, 51, 19–42. 5
- Gualandi, N., and Mantecchini, L. (2008). Aircraft Noise Pollution : a Model of Interaction between Airports and Local Communities. *International Journal of Mechanical Systems Science and Engineering*, 2(September).
- Guo, Y. C., Zhang, J. H., Chen, G., Chen, G. M., and Xie, Z. H. (2014a). Fracture behaviors of a new steel fiber reinforced recycled aggregate concrete with crumb rubber. *Construction and Building Materials*, 53, 32–39.
- Guo, Y. C., Zhang, J. H., Chen, G. M., and Xie, Z. H. (2014b). Compressive behaviour of concrete structures incorporating recycled concrete aggregates, rubber crumb and reinforced with steel fibre, subjected to elevated temperatures. *Journal of Cleaner Production*, 72, 193–203.
- Harrison, D., Grassie, S. L., Gregory, R. W. and Johnson, K. L. (2015), The dynamic response of railway track to high frequency vertical excitation. *Journal of Mechanical Engineering Science*, vol. 24, no. 2, pp. 77–90.
- Hawkins, T. G. (2014). Studies and research regarding sound reduction materials.
- Ibrahim, I. M. H. (n.d.). Waste Management of Coal Fired Power Plant : A Case Study of Tanjung Bin Power Plant. 10th Annual Waste Management Conference and Exhibition.
- Ibrahim, M. H. W., Hamzah, A. F., Jamaluddin, N., Ramadhansyah, P. J., and Fadzil, A. M. (2015). Split Tensile Strength on Self-compacting Concrete Containing Coal Bottom Ash. *Procedia - Social and Behavioral Sciences*, 195, 2280–2289.
- Idrus, M., Masirin, M., Salin, A. M., and Zainorabidin, A. (2017). Review on Malaysian Rail Transit Operation and Management System : Issues and Solution in Integration:
- Iffat, S. (2015). Relation Between Density and Compressive Strength of Hardened Concrete Concrete Research Letters, vol.6 (4)(December), 8.



- Ishak, M. B. (2002). The law of industrial waste management in Malaysia. *Waste Management and the Environment*, 643–651.
- Irwin, J.D and Graf, E.R. (1979), “Industrial noise and vibration control”, Alabama, Prentice-Hall, pp.237–240.
- Jabatan Kerja Raya (JKR) Malaysia, (2005). Standard specifications for building works
- Jamaluddin, N., Hamzah, A. F., Wan Ibrahim, M. H., Jaya, R. P., Arshad, M. F., Zainal Abidin, N. E., and Dahalan, N. H. (2016). Fresh Properties and Flexural Strength of Self-Compacting Concrete Integrating Coal Bottom Ash. *MATEC Web of Conferences*, 47, 01010.
- Janković, K., Bojović, D., Lončar, L., Stojanović, M., and Antić, L. (2018). Possibility of using bottom ash in precast concrete products, 70, 413–419.
- Jayaraman, K. A. (2005), Acoustical absorptive properties of nonwo-ovens, MSc Thesis, North Carolina State University, Raleigh, NC.
- June, J., Politecnica, U., Lee, J. C., Bradshaw, S. L., Edil, T. B., and Benson, C. H. (2010). Green Benefits of Using Coal Ashes in Pavement Construction.
- Kadam, M. P., and PATIL, D. (2013). Effect of coal bottom ash as sand replacement on the properties of concrete with different w/c ratio. *International Journal of Advanced Technology in Civil Engineering*, ISSN, (1), 2231–5721.
- Kadam, M. P., and Patil, Y. D. (2013). Effect of Coal Bottom Ash As Sand Replacement on the Properties of Concrete With Different W / C Ratio. *International Journal of Advanced Technology in Civil Engineering*, 2(1), 45–50.
- Kadir, A. A., Hassan, M. I. H., Jamaluddin, N., and Abdullah, M. M. A. B. (2016). Properties and Leachability of Self-Compacting Concrete Incorporated with Fly Ash and Bottom Ash. *IOP Conference Series: Materials Science and Engineering*, 133(1).
- Kasemchaisiri, R., Tangtermsirikul, S. (2008) Properties of Self-Compacting Concrete incorporating Bottom Ash as Partial Replacement of Fine Aggregate *ScienceAsia* 3487-95.
- Kathiravale, S., and Ahnankrishnan, J. (2007). Municipal Solid Waste - Management Cost and Opportunities. *Jurutera*, (March), 1–4.
- Katz, A. (2003). Properties of concrete made with recycled aggregate from partially hydrated old concrete. *Cement and Concrete Research*, 33(5), 703–711.
- Khalid, N., Sidek, N., and Arshad, M. F. (2013). The California Bearing Ratio (CBR) value of road sub-base aggregate mixed with bottom ash. *Malaysian Journal of Civil Engineering*, 121(1), 112–121.

- Khalid, U. A., Bachok, S., and Osman, M. M. (2014). User Perceptions of Rail Public Transport Services in Kuala Lumpur , Malaysia : KTM Komuter. *Procedia - Social and Behavioral Sciences*, 153, 566–573.
- Khan, R., and Ganesh, A. (2016). The effect of coal bottom ash (CBA) on mechanical and durability characteristics of concrete. *Journal of Building Material and Structures*, 3, 31–42.
- Kim, H., Ha, K., Jang, J., and Lee, H. (2014). Mechanical and Chemical Characteristics of Bottom Ash Aggregates Cold-bonded with Fly Ash. *Journal of the Korean Ceramic Society*, 51(2), 57–63.
- Kim, H. K., Jeon, J. H., and Lee, H. K. (2012). Flow, water absorption, and mechanical characteristics of normal- and high-strength mortar incorporating fine bottom ash aggregates. *Construction and Building Materials*, 26(1), 249–256.
- Kim, H. K., and Lee, H. K. (2011). Use of power plant bottom ash as fine and coarse aggregates in high-strength concrete. *Construction and Building Materials*, 25(2), 1115–1122.
- Kockwood, A. ., and Evans, L. (2012). Ash in lungs. How breathing coal ash is Hazardous to your health. *EarthJustice*, 150–190.
- Kou, S. C., Poon, C. S., and Etcheberria, M. (2011). Influence of recycled aggregates on long term mechanical properties and pore size distribution of concrete. *Cement and Concrete Composites*, 33(2), 286–291.
- KTMB (2019). Retrieved April 3, 2019, <http://KTMB.com>.
- Kuczmarski, M. a, and Johnston, J. C. (2011). Acoustic Absorption in Porous Materials, (March), 1–20.
- Kuo, W.-T., Liu, C.-C., and Su, D.-S. (2013). Use of washed municipal solid waste incinerator bottom ash in pervious concrete. *Cement and Concrete Composites*, 37, 328–335.
- Kurama, H., and Kaya, M. (2008). Usage of coal combustion bottom ash in concrete mixture. *Construction and Building Materials*, 22(9), 1922–1928. 8
- Kurama, H., Topçu, I. B., and Karakurt, C. (2009). Properties of the autoclaved aerated concrete produced from coal bottom ash. *Journal of Materials Processing Technology*, 209(2), 767–773.
- Kurita, T., Wakabayashi, Y., Yamada, H., and Horiuchi, M. (2007). Efforts for Noise Reduction on FASTECH360 High Speed Test Trains. *JR EAST Technical Review*, (19), 37–40.
- Lee, H. K., Kim, H. K., and Hwang, E. A. (2010). Utilization of power plant bottom ash as aggregates in fiber-reinforced cellular concrete. *Waste Management*, 30(2), 274–284.

- Lim, Z. Y., Putra, A., Nor, M. J. M., and Yaakob, M. Y. (2018). Sound absorption performance of natural kenaf fibres, 130(September 2017), 107–114.
- Liu, E. D. H. F., Liptak, B. G., Raton, B., Press, C. R. C., Liu, D. H. F., and Roberts, J. Howard C. (1999). Noise Pollution.
- Maffei, L. (2012). Influence of the design of railway noise barriers on soundscape perception, (February 2016).
- Mahzan, S., Zaidi, A. M. A., Yahya, M. N., and Ismail, M. (2009a). Investigation on Sound Absorption of Rice-Husk Reinforced Composite. Proceedings of MUCEET2009, 19–22.
- Mahzan, S., Zaidi, A. M. A., Yahya, M. N., and Ismail, M. (2009b). Investigation on Sound Absorption of Rice-Husk Reinforced Composite.
- Marto, A., and Makhtar, Ahmad mahir. (2015). Geotechnical Properties of Tanjung Bin Coal Ash Mixtures for Backfill Materials in Embankment Construction, (January 2011).
- Mercado, R. D. T., Ureta, R. M., and Templo, R. J. D. (2018). The Potential of Selected Agricultural Wastes Fibers as Acoustic Absorber and Thermal Insulator Based on their Surface Morphology via Scanning Electron Microscopy. World News of Natural Science, 20(August), 129–147.
- Mohamed, A. R., and Teong, L. K. (2010). Energy Policy for Sustainable Development in Malaysia. The Joint International Conference on “Sustainable Energy and Environment (SEE),” 028(December 2004), 940–944.
- Mohammed, S. A., and Karim, M. R. (2017). Review: Application of coal bottom ash as aggregate replacement in highway embankment, acoustic absorbing wall and asphalt mixtures. IOP Conference Series: Materials Science and Engineering, 210(1).
- Mohd Masirin, M. I., Johari, N. F., Nordin, N. H., Abdullah, A. H., and Azis, M. I. (2015). A Field Study on Urban Rail Transits in City of Kuala Lumpur: Passenger Views on Train Noise and Vibration. Applied Mechanics and Materials, 773–774(June), 839–844.
- Mohd Sahabuddin, M. F. (2012). Local Versus Global. The future of our cities: The evaluation of railway station in Kuala Lumpur. The University of Edinburgh.
- Muhardi, Marto, A., Kassim, K. A., Makhtar, A. M., Lee, foo wei, and Yap, shin lim. (2010). Engineering Characteristics of, 1117–1129.
- Murphy, E., King, E. A., and Rice, H. J. (2009). Estimating human exposure to transport noise in central Dublin, Ireland. Environment International, 35(2), 298–302.

- Muthusamy, K., Mohamad Hafizuddin, R., Mat Yahaya, F., Sulaiman, M. A., Syed Mohsin, S. M., Tukimat, N. N., Chin, S. C. (2018). Compressive strength performance of OPS lightweight aggregate concrete containing coal bottom ash as partial fine aggregate replacement. *IOP Conference Series: Materials Science and Engineering*, 342(1).
- Naganathan, S., Subramaniam, N., and Mustapha, K. N. Bin. (2012). Development of Brick Using Thermal Power Plant Bottom Ash and Fly Ash. *Asian Journal of Civil Engineering*, 13(2), 275–287.
- Naik, T. R., Singh, S. S., and Hossain, M. M. (1994). Permeability of concrete containing large amount of fly ash, (1).
- Nasidi, I. N., Ismail, L. H., Samsudin, E. M., Firdaus, M., and Khodir, A. (2018). The Effect of Different Fibre Length and Different Urea Formaldehyde ( UF ) content on Sound Absorption Performance of Empty Fruit Bunch ( EFB ). *MATEC Web of Conferences*, 150(January).
- Neubergova, K., and Tyfa, L. (2013). Railway Noise Measurements on Various Railway Superstructure Constructions, 96–101.
- Neville, A. . (2011). *Properties of concrete* (Fifth Edition). University of Leeds, England.
- Nordin, N. hafiza, Masirin, M. I. M., Ghazali, I., and Azis, M. I. (2014). Apraisal on Rail Transit Development : A Review on Train Service And Safety. *International Integrated Engineering Summit (IIES 2014)*.
- Oh, J. E, Moon, J., Mancio, M., Clark, S. M., Monteiro, P. J. M. (2010) Utilization of Yatanan Power Plant Fly Ash in Production of Building Bricks, *IOP Conference Series: Earth and Environmental Science*.
- Othmani, C., Taktak, M., Zain, A., Hantati, T., Dauchez, N., and Elnady, T. (2017). Acoustic characterization of a porous absorber based on recycled sugarcane wastes, 120, 90–97.
- Park, H. K. (2018). Indoor Noise Annoyance Due to Transportation Noise. *Journal of Asian Architecture and Building Engineering*, 7581, 149–155.
- Park, S. B., Jang, Y. Il, Lee, J., and Lee, B. J. (2009). An experimental study on the hazard assessment and mechanical properties of porous concrete utilizing coal bottom ash coarse aggregate in Korea. *Journal of Hazardous Materials*, 166(1), 348–355.
- Pedrero, A. (2005). The reverberation time of furnished rooms in dwellings, 66, 945–956.
- Prasad Koirala, M., and Buddhi Raj Joshi, E. (2017). Construction sand, Quality and supply management in infrastructure project. *International Journal of Advances in Engineering and Scientific Research*, 4(December), 2349–4824.

- Pultznarová, A., and Ižvolt, L. (2014). Structural modifications, elements and equipment for railway noise reduction. *Procedia Engineering*, 91(TFoCE), 274–279.
- Putra, A., Abdullah, Y., Efendy, H., Farid, W. M., Ayob, R., and Py, M. S. (2013). Utilizing Sugarcane Wasted Fibers As A Sustainable Acoustic Absorber. *Malaysian Technical Universities Conference on Engineering and Technology 2012, MUCET 2012 Part 2 Mechanical And Manufacturing Engineering Utilizing*, 53, 632–638.
- Radonjanin, V., Malešev, M., Marinković, S., and Al Maly, A. E. S. (2013). Green recycled aggregate concrete. *Construction and Building Materials*, 47, 1503–1511.
- Rafat Siddique. (2013). Compressive strength, water absorption, sorptivity, abrasion resistance and permeability of self-compacting concrete containing coal bottom ash. *Construction and Building Materials*, 47, 1444–1450.
- Raffaella, D., Carmine, L. and Rosario, A. R. (2009). Reverberation time measurement by the product of two room impulse responses. *Applied Acoustics*, 70(1), 229–241.
- Rafieizonooz, M., Mirza, J., Razman, M., Warid, M., and Khankhaje, E. (2016). Investigation of coal bottom ash and fly ash in concrete as replacement for sand and cement. *Construction and Building Materials*, 116, 15–24.
- Rahim, N. L., Che Amat, R., Ibrahim, N. M., Salehuddin, S., Mohammed, S. A., and Abdul Rahim, M. (2014). Utilization of Recycled Glass Waste as Partial Replacement of Fine Aggregate in Concrete Production. *Materials Science Forum*, 803(August 2015), 16–20.
- Raju, R., Paul, M. M., and Aboobacker, K. A. (2014). Strength Performance of Concrete Using Bottom Ash As Fine aggregate. *International Journal of Research in Engineering and Technology*, 2(9), 111–122.
- Ramme, B. W. (We E., and Tharaniyil, M. P. ( B. C. (2013). *Coal Combustion Product Utilization Handbook* (3rd editio). We Energies.
- Rashad, A. M. (2015). A comprehensive overview about recycling rubber as fine aggregate replacement in traditional cementitious materials. *International Journal of Sustainable Built Environment*.
- Redden, J. P. (2005). Is Train Horn Noise a Problem in your Town ?, (September).
- Rey, R., Alba, J., Arenas, J. P., and Sanchis, V. (2011). Sound absorbing materials made of recycled polyurethane foam, (January).
- Saad, M. J., and Kamal, I. (2010). Kenaf Core Particleboard and Its Sound Absorbing Properties. *Journal of Science and Technology*, 23–34.



- Saikia, N., and de Brito, J. (2012). Use of industrial waste and municipality solid waste as aggregate, filler or fiber in cement mortar and concrete. *Municipal Solid Waste*, 34, 111–162.
- Sain, P., and Kumar, E. P. (2017). Use of Coal Bottom Ash in Concrete by Replacing Sand, 6(1), 50–57.
- Sakar, S. (2013). Assessment of Noise Level In Suburban Railways of West Bengal.
- Samsudin, Rahman, W. (2016). Power Generation Sources in Malaysia : Status and Prospects for Sustainable Development *Akademia Baru Power Generation Sources in Malaysia : Status and Prospects for Sustainable Development*, (September).
- Samsudin, E. M., Ismail, L. H., Kadir, A. A., Nasidi, I. N., and Sahidah, N. (2017). Rating of Sound Absorption for EFBMF Acoustic Panels according to ISO 11654 : 1997, (December), 0–6.
- Samsudin, E. M., Ismail, L. H., Kadir, A. A., and Norfaslia, I. (2017). Thickness , density and porosity relationship towards sound thickness , density and porosity relation ship towards sound absorption per formance of mixed palm oil fiber. 24th International Congress on Sound and Vibration, (July), 0–8.
- Samsudin, E. M., Ismail, L. H., Kadir, A. A., and Salwa Sayed Mokdar, S. (2016). Comparison on acoustic performance between dust and coir form empty fruit bunches (EFB) as sound absorption material. *Jurnal Teknologi*, 5, 191–196.
- Sandhya, B. and Reshma, E. K., (2013). "A study on mechanical properties of cement concrete by partial rreplacement of fine aggregate with bottom ash". *International Journal of Students Research in Technology and Management*, 1(December), 591–597.
- Schwarcz, S. (2003). Public Transportation in Kuala Lumpur, Malaysia Public.
- Selamat, F. ., and Rahim, F. L. Ab. (2018). Developing Noise Maps to Monitor Railway Train noise at Four Different Keretapi Tanah Melayu (KTM) Station. *International Journal of Automotive and Mechanical Engineering*, 15(2), 5377–5388.
- Shafie, S. M., Mahlia, T. M. I., and Masjuki, H. H. (2013). Life cycle assessment of rice straw co- fi ring with coal power generation in Malaysia, 57(Energy), 284–294.
- Shahidan, S., Maarof, M. Z., Izzati, N., and Ramzi, R. (2017). Existing Noise Level at Railway Stations in, 09012.
- Shahidan, S., Maarof, M. Z. M., Raihan Ramzi Hannan, N. I., and Ali, N. (2017). Existing Noise Level at Railway Stations in Malaysia. In *MATEC Web of Conferences* (Vol. 103)

- Siddique, R., Aggarwal, P., and Aggarwal, Y. (2012). Influence of water/powder ratio on strength properties of self-compacting concrete containing coal fly ash and bottom ash. *Construction and Building Materials*, 29, 73–81.
- Siddique, R., and Cachim, P. (2018). *Waste and Supplementary Cementitious Materials in Concrete: Characterisation, Properties and Applications*. Woodhead Publishing.
- Sieber, C., Ragettli, M. S., Brink, M., Olaniyan, T., Baatjies, R., Saucy, A., ... Dalvie, M. A. (2018). Comparison of sensitivity and annoyance to road traffic and community noise between a South African and a Swiss population. *Environmental Pol*, 241, 1056–1062.
- Sikora, J., and Turkiewicz, J. (2010). Sound absorption coefficients of granular materials. *Mechanics and Control*, 29(3), 149–157.
- Silva, R. V, De Brito, J., and Dhir, R. K. (2015). Tensile strength behaviour of recycled aggregate concrete. *Construction and Building Materials*, 83, 108–118.
- Singh, A., and Singh, V. (2017). Effect on Compressive and Split Tensile Strength of Concrete by Partial Replacement with Coal Bottom Ash. *International Journal for Research Trends and Innovation*, 2(11), 42–46.
- Singh, M. (2015). Effect of coal bottom ash on strength and durability properties of concrete, (951002002).
- Singh, M., and Siddique, R. (2013). Effect of coal bottom ash as partial replacement of sand on properties of concrete. *Journal of Cleaner Production*, 112, 620–630.
- Singh, M., and Siddique, R. (2014a). compressive strength, drying shrinkage and chemical resistance of concrete incorporating coal bottom ash as partial or total replacement of sand. *Journal of Cleaner Production*, 112, 620–630.
- Singh, M., and Siddique, R. (2014b). Strength properties and micro-structural properties of concrete containing coal bottom ash as partial replacement of fine aggregate. *Construction and Building Materials*, 50, 246–256.
- Singh, M., and Siddique, R. (2014c). Strength properties and micro-structural properties of concrete containing coal bottom ash as partial replacement of fine aggregate, 50, 246–256.
- Singh, M., and Siddique, R. (2015). Properties of concrete containing high volumes of coal bottom ash as fine aggregate. *Journal of Cleaner Production*.
- Singh, M., and Siddique, R. (2016a). Effect of coal bottom ash as partial replacement of sand on workability and strength properties of concrete. *Journal of Cleaner Production*, 112, 620–630.

- Singh, M., and Siddique, R. (2016b). Effect of coal bottom ash as partial replacement of sand on workability and strength properties of concrete. *Journal of Cleaner Production*, 112, 620–630.
- Skariah, B., and Gupta, R. C. (2016). A comprehensive review on the applications of waste tire rubber in cement concrete, 54, 1323–1333.
- Soeta, Y., and Shimokura, R. (2013). Survey of interior noise characteristics in various types of trains. *Appl. Acoust. (UK)*, 74(10), 1160–1166.
- Sun, P., and Guo, Z. (2015). Sintering preparation of porous sound-absorbing materials from steel slag. *Transaction of Nonferrous Metals Society of China*, 25(September 2014), 2230–2240.
- Suruhanjaya Tenaga (Energy Commission). (2018). *The Transition: Strengthening the Future of Energy in Malaysia* (Vol. 14).
- Syahrul, M., Sani, M., Muftah, F., and Muda, Z. (2010). The Properties of Special Concrete Using Washed Bottom Ash ( WBA ) as Partial Sand Replacement. *International Journal of Sustainable Construction Engineering and Technology*, 1(2), 65–76.
- Syarafuddin, M., and Shariff, B. I. N. (2016). Evaluation of noise level in coach and train station at lrt kelana jaya line, (April).
- Tang, X., Zhang, X., Zhang, H., Zhuang, X., and Yan, X. (2018). Corn husk for noise reduction : Robust acoustic absorption and reduced thickness, 134(January), 60–68.
- Tarmudi, Z., Abdullah, M. L., and Osman MD Tap, A. (2009). *An Overview of Municipal Solid Wastes Generation In Malaysia*, (December).
- Thompson, D. (2014). *Railway Noise and Vibration : the Use of Appropriate Models To Solve Practical Problems*. The 21 St International Congress on Sound and Vibration, (July), 13–17.
- Thorneycroft, J., Orr, J., Savoikar, P., and Ball, R. J. (2018). Performance of structural concrete with recycled plastic waste as a partial replacement for sand. *Construction and Building Materials*, 161, 63–69.
- Tiwari, A. V, Kadu, P. a, and Mishra, A. R. (2013). Study of Noise Pollution Due To Railway and Vehicular Traffic at Level Crossing and Its Remedial Measures, (4), 16–19.
- Tong, Y. G., Abu Bakar, H., Mohd. Sari, K. A., Ewon, U., Labeni, M. N., and Fauzan, N. F. A. (2017). Effect of urban noise to the acoustical performance of the secondary school's learning spaces – A case study in Batu Pahat. *IOP Conference Series: Materials Science and Engineering*, 271, 012029.



- TOPÇU, I. B., and BILIR, T. (2008). Effect of Bottom Ash as Fine Aggregate on Shrinkage Cracking of Mortars. *ACI Materials Journal*.
- Vasudev, S., and Atri, S. (2014). Sound and Solid Surface, *Applied Acoustics*, 72(4), 221–225.
- Vasudevan, G. (2013). Absorption, *Applied Acoustics*, 24–33.
- Wearing, C., J.D.Nairn, and Birch, C. (2004). An assessment of Tarong bottom ash for use on agricultural soils. *Developments in Chemical Engineering and Mineral Processing*, 12(5–6), 531–543.
- Wilk, G., and Włodarczyk, Z. (2017). Temperature oscillations and sound waves in hadronic matter. *Physica A*, 486, 579–586.
- Wongkeo, W., Thongsanitgarn, P., Pimraksa, K., and Chaipanich, A. (2012). Compressive strength, flexural strength and thermal conductivity of autoclaved concrete block made using bottom ash as cement replacement materials. *Materials and Design*, 35, 434–439.
- Wongpa, J., Kiattikomol, K., Jaturapitakkul, C., and Chindaprasirt, P. (2010). Compressive strength, modulus of elasticity, and water permeability of inorganic polymer concrete. *Materials and Design*, 31(10), 4748–4754.
- Xie, J. (2015). Road traffic noise mapping in Guangzhou using GIS and GPS. *Applied Acoustics*, 87, 94–102.
- Yaprak, H., Memis, S., and Kaplan, G. (2017). Effect of Industrial Wastes as Replacement of Fine Aggregate on Properties of Concrete. *Journal of Scientific and Engineering Research*, 4(12), 228–235.
- Yüksel, I., and Genç, A. (2015). Properties of Concrete Containing Nonground Ash and Slag As Fine Aggregate. *ACI Materials Journal*.
- Zainal Abidin, N. E., Wan Ibrahim, M. H., Jamaluddin, N., Kamaruddin, K., and Hamzah, A. F. (2015). The Strength Behavior of Self-Compacting Concrete Incorporating Bottom Ash as Partial Replacement to Fine Aggregate. *Applied Mechanics and Materials*, 773–774, 916–922.
- Zelan (2019). Retrieved April 3, 2019, <http://zelan.com>.
- Zhang, X. (2010). Applicable Directivity Description of Railway Noise Sources.
- Zhang, X. (2014). A simplified approach for evaluating noise impact from high-speed lines, 1–7.